



# PALFOAM™

Low Weight Flat Foamed PVC Sheet



## Overview

PALFOAM offers easy-to-handle foamed PVC in a cost-efficient version. Its bright, consistent and smooth surface provides a good background for printing and laminating in high quality stands and displays.

PALFOAM is flexible, versatile and extremely convenient to work with. It can be cut and fabricated using conventional tools and equipment.

## Main Benefits

- Value-oriented for cost sensitive projects
- Slightly lighter weight than standard PALIGHT Foam PVC sheet
- Good ink adhesion and print quality
- Bright, smooth and uniform surface
- High insulation
- Easily worked with conventional tools, prints and paints
- Can be easily bonded, vacuum formed, nailed and bolted
- High chemical resistance
- Low water absorption
- Non-toxic

## Typical Applications

- Portable displays
- Point-Of-Purchase displays
- Signs
- Displays
- Interior decoration
- Exhibition boards
- Display cladding



[www.palram.com](http://www.palram.com)



## Standard Dimensions

Specification	Value
Thickness	2, 3, 4, 5, 6, 8, 10mm
Dimensions*	2030x3050 1560x3050 1220x3050
Color	White

\* Other dimensions are available upon request.

## Product Range

Product	Description
PALIGHT®	Flat foamed PVC sheet with matte finish, available in a wide range of standard and special thicknesses and designer colors.
PALFOAM™	Cost-effective, white only, light weight flat foamed PVC sheet.
PALIGHT® Print	Flat foamed PVC sheet made specifically to cost effectively meet the stringent requirements of large format print imaging industry.
PALFOAM™ LW	Low weight, white only, flat foamed PVC sheet for general purposes.

## Typical Physical Properties\*

Property	Method	Conditions	Units	Value
Density	D-792		g/cm <sup>3</sup>	0.50-0.57
Water absorption	D-570	24hr. @ 23°C	%	0.28
Flexural modulus	D-790	1mm/min.	MPa	700-1100
Hardness	Shore D			78-84
Izod impact strength	D-265		J/m	30-66
Service temperature range			°C	-10 to 55
Heat deflection temperature (H.D.T)	D-648	Load: 1.82MPa	°C	58-61
Vicat softening temp	D-1525	Load: 1kg	°C	75-77
Coefficient of linear thermal expansion	D-696		cm/cm °C	6.7x10 <sup>-5</sup>
Thermal conductivity	C-177		W/mK	0.07
White index	D-792		WI	90
Surface resistance	D-257		Ohm	5X10 <sup>15</sup>
Volume resistance	D-257		Ohm-cm	2X10 <sup>16</sup>

\*Information applies to 3-10mm sheets.



**PALRAM H.Q.**  
Tel: +972 4 8459900  
Fax: +972 4 8444012  
palram@palram.com

**PALRAM EUROPE LTD.**  
Tel: +44 1302 380777  
Fax: +44 1302 380778  
sales.europe@palram.com

**PALRAM AMERICAS**  
Tel: +1 610 2859918  
Fax: +1 610 2859928  
palramamericas@palram.com



61152-07.2016

In as much as Palram Industries has no control over the use to which others may put the material, it does not guarantee that the same results as those described herein will be obtained. Each user of the material should make his own tests to determine the material's suitability for his own particular use. Statements concerning possible or suggested uses of the materials described herein are not to be construed as constituting a license under any Palram Industries patent covering such use or as recommendations for use of such materials in the infringement of any patent. Palram Industries or its distributors cannot be held responsible for any losses incurred through incorrect installation of the material. In accordance with our company policy of continual product development you are advised to check with your local Palram Industries supplier to ensure that you have obtained the most up to date information.

©2011 Palram Industries Ltd. | PALFOAM is a trademark of Palram Industries Ltd.

