

SUNTUF® EZ GLAZE Data Sheet

Profile: 138(36-600-1273)




05/05/2019

Product Description:

- SUNTUF Co-extruded UV protection on one side.
- SUNTUF UV2 Co-extruded UV protection on two sides.

Profile drawing:



General properties:

Profile (mm)	Thickness (mm)	Length (m)	Overall width (mm)	Cover Width (mm)	Side-Lap (%)
600/36	3.0	1.8 – 7.2	1273	1200	5

Load / Span Data

Maximum Roof Span (mm)		
Load (Kpa)	3.0 mm	
	Mid Span	End Span
0.75	2050	1540
1.0	1850	1390
1.25	1700	1275
1.50	1600	1200
1.75	1550	1160
2.0	1450	1090

- The specified dimensions do not supersede the requirements of local construction codes.
- The given spans are according to deflections criterion of L/20, and minimum slope of 10%.
- The maximum roof spans are based on calculation model and practical testing.
- The mentioned load refers to wind and snow load only.
- For vertical application spans can be increased by 10%.

Curved roof

- Minimum curving radius – 15 m.

SUNTUF® EZ GLAZE Data Sheet

Profile: 138(36-600-1273)



05/05/2019

Typical Properties

Property	Standard	Conditions	Unit	Value
Density	ASTM D792	-	g/cm ³	1.2
Heat Deflection Temperature	ASTM D648	1.82 MPa	°C	130
Service Temperature (Short term)	-	-	°C	-50 to 120
Service Temperature (Long term)	-	-	°C	-50 to 100
Coefficient of Linear Thermal Expansion	ASTM D696	-	cm/cm °C	6.5 X 10 ⁻⁵
Thermal Conductivity	ASTM C177	-	W/mK	0.21
Tensile Strength at Yield	ASTM D638	10 mm/min	MPa	62
Tensile Strength at Break	ASTM D638	10 mm/min	MPa	65
Elongation at Yield	ASTM D638	10 mm/min	%	7
Elongation at Break	ASTM D638	10 mm/min	%	>90
Tensile Modulus of Elasticity	ASTM D638	10 mm/min	MPa	2300
Flexural Strength	ASTM D790	1.3 mm/min	MPa	93
Flexural Modulus	ASTM D790	1.3 mm/min	MPa	2600
Impact Falling Weight (E-50)	ISO 6603/1	3mm sheet	J	158
Rockwell Hardness	ASTM D785		R Scale	125R
Light Transmission	ASTM D1003	Clear	%	90
Haze	ASTM D1003		%	<0.5
Yellowness Index	ASTM D1925			<1

SUNTUF® EZ GLAZE Data Sheet

Profile: 138(36-600-1273)



05/05/2019

*Please refer to Technical guide for more details.